Amendments to the Code of Practice for Structural Use of Glass 2018

Item	Current version	Amendments
1. Clause 7.1.1	The structural performance of a structural sealant depends	The structural performance of a structural sealant depends
2 nd paragraph ¹	on a number of factors such as risks to building occupants	on a number of factors such as risks to building occupants
	and pedestrians, long-term durability, degree of redundancy,	and pedestrians, long-term durability, degree of redundancy,
	nature of applied loads, and quality control during	nature of applied loads, and quality control during
	fabrication and erection. Façade system or glass element	fabrication and erection. Façade system or glass element,
	with structural sealant glazing application shall be designed	located where any point of the glass pane installed is at a
	to prevent any fall of glass pane in the event of bond failure	height 5 m or more above the finished floor level of the
	in the structural sealant. Retaining devices for such	accessible area on either side of the glass pane, fixed by
	structural sealant glazing in the form of feature capping,	structural sealant on four sides shall be designed to
	angle, bracket or insert, etc. shall be designed and	prevent any fall of glass pane in the event of bond failure in
	constructed at the top and the bottom of the glass pane for	the structural sealant. Retaining device in the form of
	the added purpose of restraining the glass pane from	feature capping, angle, bracket or insert, etc. shall be
	dislocation or falling in case of bond failure of structural	designed and constructed at any two opposing edges of the
	sealant. The self-weight of the glass panes shall be	glass pane for the added purpose of restraining the glass
	mechanically supported by setting blocks.	pane from dislocation or falling in case of bond failure of
		structural sealant. The strength of such retaining device
		and associated glass panes shall be capable to resist 37% of
		the design wind pressure acting on the glass pane
		multiplying with a partial load factor of 1.0. The design
		wind pressure is taken as the wind reference pressure in

Annex

			accordance with the Code of Practice on Wind Effects in Hong Kong 2019 without applying any adjustment factors. The self-weight of the glass panes shall be mechanically supported by setting blocks.
2.	Clause 7.5.1 2 nd paragraph ²	Weather strips, glazing gaskets and glazing blocks shall be manufactured from extruded silicone rubber, Ethylene Propylene Diene Monomer (EPDM) rubber or other gasket material such as neoprene and Thermoplastic Elastomer (TPE) compatible with silicone sealant. Gaskets shall be provided on both sides of the vent glass unless it is structurally glazed. All gaskets/ weather seals/ spacers shall have continuous mechanical engagement to the framing members.	Weather strips, glazing gaskets and glazing blocks shall be manufactured from extruded silicone rubber, Ethylene Propylene Diene Monomer (EPDM) rubber or other gasket material such as neoprene and Thermoplastic Elastomer (TPE) compatible with silicone sealant. Gaskets shall be provided on both sides of the glass pane unless it is structurally glazed. All gaskets/ weather seals/ spacers shall have continuous mechanical engagement to the framing members.
3.	Clause 9.4 3 rd paragraph ²	Deglazing test is a method of quality inspection used to confirm if the sealant application has strictly followed the recommendations outlined in the sealant manufacturer's print review and adhesion test report. Deglazing test should be carried out in accordance with the sealant manufacturer's suggested percentage of total number of structurally glazed glass panes to ensure the on-site structural glazing quality of the factory structural glazing	Deglazing test is a method of quality inspection used to confirm if the sealant application has strictly followed the recommendations outlined in the sealant manufacturer's print review and adhesion test report. Deglazing test should be carried out in accordance with the sealant manufacturer's suggested percentage of total number of structurally glazed glass panes to ensure the on-site structural glazing quality or the factory structural glazing

	quality before transportation to the site for installation.	quality before transportation to the site for installation.	
	The inspection should include the following:	The inspection should include the following:	
4. Annex C - C2 ³	In computing the effective torsional rigidity of beams of	In computing the effective torsional rigidity of beams of	
	solid rectangular cross-section, the value of the torsional	solid rectangular cross-section, the value of the torsional	
	moment of inertia (J) may be taken as	moment of inertia (J) may be taken as	
	$J = \frac{db^3}{3} (1 - 0.63 \frac{b}{d})$	$J = \frac{dt^3}{3} (1 - 0.63 \frac{t}{d})$	
	where d and b are the depth (fin thickness) and breadth of	where d and t are the depth and thickness of the glass fin	
	the fin respectively.	respectively.	
	G and E are taken as 28,700 N/mm ² and	G and E are taken as 28,700 N/mm ² and	
	70,000 N/mm ² for glass fins.	70,000 N/mm ² for glass fins.	
Legends: Amended			

Deleted

¹ The design requirements for retaining device and associated glass panes to cope with the situation of bond failure of structural sealant are elaborated.

² A typo is corrected.

³ The symbol of glass fin thickness in the equation is revised.